



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA

PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉF.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



SPM – 3876 ANTIOXIDANT SHOP PRIMER S/R

PRODUCT DESCRIPTION:

- **DEFINITION:** Universal shop primer ideal for automatic application systems and continuous or conventional.
- **USE:** It is used as a first protective coat after the blasting.
- **PROPERTIES:** Excellent drying, good weldability, and strong temporary protection to the weather.

TECHNICAL INFORMATION

Aspect.....	SATIN-MATT
Color.....	RED
Density.....	1,45 +/- 0.05 Kg/Lt.
Volume solids.....	48%
Recommended thickness.....	40 - 50 MICRON DRY FILM
Theoretical performance.....	19.2 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	4 MINUTES
Overall.....	15 MINUTES
Repaint.....	4 HOURS
“Q” VALUE.....	33%

APPLICATION INSTRUCTIONS:

- **Method**
Automatic or conventional application.
- **Dilution**
At use or if necessary use our D-302 Solvent or D-308 fast Solvent.
- **Cleaning**
After use, clean all equipment with our Universal Solvent W.
- **Storage**
One year at a temperature between 5 - 35 ° C without opening the container.

SURFACES PREPARATION:

It should be applied immediately after a blasting SA 2 ½.

HYGIENE AND SECURITY:

- Flammable.
 - May cause sensitization by skin contact.
 - Harmful by inhalation and skin contact.
 - Keep container in a well ventilated area.
 - In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
 - In case of accident or illness, seek medical advice immediately (if possible show the label).
 - Use only in well ventilated areas.
 - Use appropriate clothing and gloves and eye and face protection.
- Contains Xylene (mixed isomers).

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.