



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA  
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16  
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## HIGH THICKNESS CHLORINATED RUBBER INTERMEDIATE LAYER

### PRODUCT DESCRIPTION:

- **DEFINITION:** Painting made with chlorinated rubber resins, designed for use as intermediate coat in chlorinated rubber painted systems.
- **USE:** As barrier layer on chlorinated rubber systems for steel protection in aggressive industrial environments.
- **PROPERTIES:** Excellent chemical resistance. It has fast drying, high thickness and fulfills SSPC-SP-18 standard.

### TECHNICAL INFORMATION

Aspect.....	SEMIGLOSS
Color.....	RAL 1001 CREAM.
Density.....	1,3 Kg/Lt
Viscosity.....	80 - 100 K.U.
Volume solids.....	44%
Recommended thickness.....	100 micron
Theoretical performance.....	4.4 M <sup>2</sup> /Lt
Drying 20 °C/70% RH	
Touch.....	30 MINUTES
Overall .....	12 HOURS
Repaint .....	ONCE DRIED

### APPLICATION INSTRUCTIONS:

- **Method**  
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**  
If necessary use our D - 307 Solvent.
- **Cleaning**  
After use, clean all equipment with our S. G. Solvent.

### SURFACES PREPARATION:

The surface to be painted must be clean of dust and grease, and treated with an appropriate anticorrosive primer to the painted system.

### HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 - 562.84.69.

### Comment

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.