



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA

PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



ESCLOR - VARNISH FIREPROOF VARNISH

PRODUCT DESCRIPTION:

- **DEFINITION:** Fireproof varnish of one component made with special resins which not burn, it supports the fire actions and is flame resistant.
- **USE:** To decorate and protect wood surfaces and maintain its reaction to fire.
- **PROPERTIES:** Very ease to apply. It has elastic finish and high hardness and does not promote the spread of fire.

TECHNICAL INFORMATION

Aspect.....	MATTE, SATIN and GLOSS
Color.....	COLORLESS and WOOD TONES
Density.....	0,97 Kg/Lt.
Viscosity.....	50" FORD CUP N° 4
Volume solids.....	45 %
Recommended thickness.....	20 - 25 MICRONS
Theoretical performance.....	18 M²/Lt.
Drying 20 °C/70% RH	
Touch.....	1 - 2 HOURS
Overall	8 HOURS
Repaint	24 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our D-302 solvent.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

SURFACES PREPARATION:

Once sanded the surface and properly prepared the wood, clean and remove all traces of dust, grease and dirt. Then apply a first diluted layer which acts as a sealer and then one or two layers of fireproof varnish performing a sanding between coats.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.