



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA

PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



RX – 24 – LATEX ALKYL

TYPE: 240 T. INTUMESCENT

PRODUCT DESCRIPTION:

- **DEFINITION:** Water emulsion of a synthetic homopolymer of general use as bottom coat in interior surfaces paintings.
- **USE:** It is base as primer for intumescent and fireproof treatments systems. To paint on walls, ceilings and all types of building materials for later be treated with plastic paint or tempera. Can also be used, on interior surfaces, as varnish finish on the paintings mentioned above, to brighten and enhance its washability.
- **PROPERTIES:** Shiny appearance. It reinforces the interior plastic paints washability. Seal building materials even when diluted, giving hardness, filling and absorption elimination to the bottom paint.

TECHNICAL INFORMATION

Aspect.....	SATIN
Liquid color.....	WHITISH
Finish color.....	COLORLESS
Density.....	1 Kg/Lt.
Film formation min. temperature...	7° C
Theoretical performance.....	12 M ² /Kg.
Drying 20 °C/70% RH	
Touch.....	2 HOURS
Repaint.....	8 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun or Air-Less.
- **Dilution**
If necessary use only water.
- **Cleaning**
After use, clean all equipment with water.

SURFACES PREPARATION:

It had to be removed all the material bad attached by brushing or scratching. Then as a sealant, prepare a solution bearing a part of **RX-24** and 2-3 parts of water. If the purpose is to shine and protect the finish, mix 1 part of **RX-24** and 2 parts of water.

HYGIENE AND SECURITY:

- Non-flammable product.
- Because contain no toxic product, no precautions are necessary in this regard.
- If applied by spray mask is recommended.
- It should not apply in very cold weather where there are temperatures below or close to 0 ° C.
- Preserves the paint can of frost.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.