



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959
POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)
TELÉF.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS
E-mail: eupines@terra.es



ESMALTPOLY 2/C – 767 SPECIAL FOR FACADE

PRODUCT DESCRIPTION:

- **DEFINITION:** Aliphatic Acrylic Polyurethane coating of two components special for facades, frontons and courtyards Pure Aliphatic Isocyanate catalyzed for maximum outside protection and prevent yellowing.
- **USE:** As termination coating for facades with cement load, concrete, asbestos cement and in special polyurethane processes for protection of elements exposed to weathering, fungi, industrial atmospheres, marine environment, aggressive environments, oil spills, solvents, acids and alkalis. Highly recommended for bathrooms and gymnasiums showers, etc. where humidity stains are produced by different types of fungus.
- **PROPERTIES:** High gloss finish, satin or matt with extraordinary color retention and film hardness that allows it to act as anti dust. It has high mechanical resistance to impact, abrasion and environment. Has excellent chemical resistance to solvents and fungus.

TECHNICAL INFORMATION

Aspect..... GLOSS, SATIN, MATTE
 Color..... ALL RAL CHART F3
 Density..... 1.30 Kg/Lt
 Proportion and lifetime mixing..... 4/1 10 to 12 HOURS
 Viscosity..... 65 – 70 K.U.
 Volume solids..... 52 %
 Recommended thickness..... 40 - 50 MICRONS
 Theoretical performance..... 12 - 14 M²/Lt
 Drying 20 °C/70% RH
 Touch..... 2 HOURS
 Repaint 24 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our Polyurethane Solvent.
- **Cleaning**
After use, clean all equipment with our Polyurethane Solvent.

SURFACES PREPARATION:

It must be applied over a properly sealed surface, clean, dry and free of grease. On all surfaces previously apply a good coat of our VITREN - 230 left to dry for 24 hours before applying ESMALTPOLY - 767. Apply to entire surface two coats of ESMALTPOLY - 767 crosswise with an interval of 4 to 8 hours between each coat. The peeling areas, if any, is necessary repair it.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.