



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16
FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



J - 13

INVISIBLE WATER REPELLENT

PRODUCT DESCRIPTION:

- **DEFINITION:** Product specially formulated for waterproof vertical surfaces constructed by brick, sandstone, natural stone, concrete, tile, etc.
- **USE:** As invisible waterproofing in different areas outlined above.
- **PROPERTIES:** Great capacity of impregnation. It prevents efflorescence of soluble salts. It reduces the thermal conductivity, thus originating better thermal insulation. It attenuates the tendency of walls to get dirty. Avoid humidity. Harden the surfaces.

TECHNICAL INFORMATION

Aspect.....	INVISIBLE
Color.....	COLORLESS
Density.....	0,79 Kg/Lt.
Viscosity.....	11" FORD CUP N° 4
Recommended thickness.....	15 MICRAS
Theoretical performance.....	8 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	1 HOURS
Overall.....	2 HOURS
Repaint.....	4 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
Applies to supply viscosity.
- **Cleaning**
After use, clean all equipment with our S.G. Solvent.

SURFACES PREPARATION:

The walls should be clean and dry. The cleaning of the facade must be done, if possible, by sandblasting or steam. Surfaces must be dry, so you must wait at least 24 hours after it have rained, and in case of cleaning with pressurized water, wait three days of dry weather. The surfaces of fresh concrete and joint's mortar should be forged (3 to 4 week minimum) before the application of J-13 INVISIBLE WATER REPELLENT. In cases of very porous surfaces, shall be proceed the application of a second or third layer. Generally we recommend applying two coats.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 - 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.