



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA

PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



MONOGAL

PRODUCT DESCRIPTION:

- **DEFINITION:** Monocomponent paint for galvanized surfaces.
- **USE:** Coating for all types of galvanized, whether cold or hot as single painting.
- **PROPERTIES:** Excellent adhesion on any galvanized substrate for inside and outside, with good weather resistance without loss of brightness.
If necessary it can be applied directly on iron completely oxide free, thanks to its high antioxidant power.

TECHNICAL INFORMATION

Aspect.....	BRIGHT, SATIN, MATTE
Color.....	ACC/ORDER
Density.....	1.1 +/- 0.05 Kg. / Lt. (WHITE)
Volume solids.....	MIN. 35 %
Recommended thickness.....	60 MICRAS
Theoretical performance.....	5.87 M ² /Lt.
Drying 20 °C/70% RH	
Touch.....	20 MINUTES AT 20° C
Overall.....	1.5 HOURS AT 20° C
Repaint.....	10 HOURS AT 20° C
Q value.....	38% (WHITE)

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun.
- **Dilution**
If necessary please use our polyurethane Solvent.
- **Cleaning**
After use, clean all equipment with our S. G. Solvent.
- **Storage**
Under cover for 1 year at room temperature and without freezing.

SURFACES PREPARATION:

- The surface must be completely free of grease, oil, dust or other contamination.
- **AVERAGE WARRANTY:** correctly applied with one coat, two years. And with two coats, 4 years.

HYGIENE AND SECURITY:

- R11.....Easily flammable.
- R65.....Harmful: if swallowed may cause lung damage.
- R20/21..... Harmful by inhalation and skin contact.
- R36/37/38... Irritating to eyes, skin and respiratory tract.
- R23.....Do not breathe vapors or aerosols.
- R62.....If swallowed do not induce vomiting: seek medical advice immediately and show its container or label: Toluene, Xylene (mixed isomers) or call the National Toxicology Institute 91 - 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.