



# EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA

PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉF.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



## OXIDOL - 111

### PRODUCT DESCRIPTION:

- **DEFINITION:** It is a mixture of acidic compounds that quickly achieve oxidative effects in metals such as iron and steel, without damaging the base support.
- **USE:** Used when wants to oxidize metal sheets in a short period of time, with good aesthetic presence and subsequent protection with colorless varnishes, mainly of pure aliphatic acrylic polyurethane of high resistance in outside environments.

### TECHNICAL INFORMATION

Aspect.....	TRANSPARENT
Color.....	COLORLESS
Density.....	1,26 Kg/Lt.
Viscosity.....	25" FORD CUP N° 4
Solvent.....	WATER
Theoretical performance.....	10 M²/Lt.

### APPLICATION INSTRUCTIONS:

It can be applied directly on the plate to oxidize, or after a light brushing, to standardize the appearance of rust. The application can be made with millet broom, brush or roller.

Later it should apply two coats of BARNIPOLY 2/C HIGH STRENGTH, which will confer an excellent protection to the weather. In many cases it is recommended the application of a third coat.

### HYGIENE AND SECURITY:

- Being an acid product should avoid contact with skin and eyes. In case of any neglect, wash the affected area with water; always consult your doctor or the National Toxicology Institute 91 - 562.84.69.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.

### Comments

- \* When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- \* The solvent addition proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- \* Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.