



EUROPEA DE PINTURAS ESPECIALES, S.L.

C.I.F. B/33.124.959

POLÍGONO DE SALCEDO - 33120 PRAVIA
PRINCIPADO DE ASTURIAS (ESPAÑA)

TELÉFOS.: 98 582 21 39 / 98 582 20 61 / 98 582 22 16

FAX 98 582 22 16 - APARTADO 311 - 33400 AVILÉS

E-mail: eupines@terra.es



ELECTROSTATIC VINYL ALUMINUM

PRODUCT DESCRIPTION:

- **DEFINITION:** It is a painting produced based on vinyl nature resins and pigmented with aluminum paste with high covering power.
- **USE:** For surfaces exposed to weathering where there may be presence of gaseous emission type acid. Also for parts exposed to all types of grease and oils.
- **PROPERTIES:** Very fast drying, enabling agile handling of pieces in the workshop. It has excellent anchorage on all kind of support, high covering power, even at low film thicknesses.

TECHNICAL INFORMATION

Aspect.....	GLOSS
Color.....	ALUMINUM GRAY
Density.....	0.89 Kg/Lt.
Viscosity.....	70" FORD CUP N° 4
Volume solids.....	20 %
Recommended thickness.....	20 MICRONS
Theoretical performance.....	10 M ² /Lt.
Conductivity.....	400 – 500 KΩ
Drying 20 °C/70% RH	
Touch.....	5 MINUTES
Overall	2 HOURS

APPLICATION INSTRUCTIONS:

- **Method**
Brush, Roller, Airbrush gun, Air-Less.
- **Dilution**
If necessary use our Retardant Vinyl Solvent.
- **Cleaning**
After use, clean all equipment with our Retardant Vinyl Solvent.

SURFACES PREPARATION:

- Cleaning the surface to be treated by blasting up grade S to 2 ½ of the Swedish Standard SIS 055.900.
- In the case of small parts or can not be done this degree of cleanliness, should be cleaned with strong solvents, before apply Electrostatic Vinyl Aluminum.

HYGIENE AND SECURITY:

- Being a flammable product, keep away from sparks and flames.
- It is recommended the most appropriate respiratory protection to each case by the corresponding mask.
- Avoid prolonged inhalation of solvent vapors.
- During the application have adequate ventilation and maintain a constant air renewal.
- Avoid eye and skin contact, if product comes in contact with skin, wash with soap and water.
- If the product splashes eyes, rinse with water several times; always consult your doctor or the National Institute of Toxicology, Phone Number 91 – 562.84.69.

Comments

- * When performance practical calculation take place it is necessary to be considered product losses by surface irregularities and application system.
- * The solvent addiction proportionally modifies the solid content in the paint and therefore the thickness of wet film.
- * Our Technical Department will be pleased to answer as many as questions that you are planning to ask.

Our technical service is at your disposal for further information in this booklet as well as to advise on special treatments, systems, process and the best products, according to the surface, environments and needs they wish to cover.

In this sheet, we just trying to inform and advice to our best knowledge, based on experience and research. We cannot be responsible for the consequences of using this product when application conditions and circumstances fall out of our reach and control.